



TACKY TAPE®

SM5700

Poly-Glaze® Tape Sealant

TECHNICAL DATA

PRODUCT DESCRIPTION:

SM5700 Poly-Glaze® is a 100% solids compound that is a blend of polyisobutylene polymer and highly crosslinked butylpolymer. It is supplied as a preformed sealant in rope form. The product can be described as a dense, tacky, rubber-like compound.

BASIC USES:

SM5700 Poly-Glaze® Tape Sealant is used for sealing and bedding vision lites and panels found in fenestration details. It can also be used to seal other joint details found in assembly and fabrication operations where a high-solids, non-drying preformed sealant is required. SM5700 Poly-Glaze® may be factory or field applied. No primers are required to obtain adhesion. Clean substrates are required. The tape exhibits excellent weatherability when exposed to ultraviolet and infrared radiation, atmospheric hydrocarbon contamination and extremes in temperature. Will not craze acrylic or polycarbonate plastic surfaces.

LIMITATIONS:

Not recommended for:

- a) Joints that will be subjected to prolonged periods of water submersion.
- b) Joints that are contaminated with oil, grease, wax, lacquer films, corrosion, bitumens, uncured or cured solvent-trapped wood treatment, damp, wet or frost bearing surfaces.

INSTALLATION:

Preparation:

- a) A clean dry uncontaminated surface is required for optimum sealant performance. Joints must be inspected prior to application and any condition that could cause sealant failure should be reported to the general contractor and architect.
- b) Cleaning of substrate surfaces to remove oil films, protective coating, and atmospheric contamination is easily accomplished with a degreasing solvent like xylene, toluene or methyl ethyl ketone. The use of these solvents (or other solvents) may be hazardous to your health. Use only in well ventilated areas. **KEEP AWAY FROM OPEN FLAME.** Read all labeling before use and follow solvent manufacturer's recommendations and instructions for safe handling.
- c) Inspect all sash to assure that openings are square, plumb and properly anchored to assure face and edge clearances. Ventilators and operating sash must be adjusted and glazed in closed position.
- d) Seal all butt and miter joints in frame joinery with SM5504 Narrow Joint Sealant prior to tape application.

TAPE APPLICATION:

- a) Position tape approximately 1/32 of an inch below the sight line of the fixed stop. Avoid running one continuous length of tape around the entire opening. Do not lap adjoining lengths of tape. Butt the tape ends together, tool forming a molded-type corner. Then seal the joint with SM5504 Narrow Joint Sealant. This technique will allow intimate contact of tape and glass or panel surfaces.

TYPICAL PROPERTIES		
Characteristic	Result	Test Method
Percent Solids:	100%	Standard Vacuum Method
Tensile Yield:	10-20 psi (0.06-0.13 N/mm ²)	AAMA 800.92
Elongation:	300-500%	ASTM D 1191
Sag:	None	AAMA 800-92
Vehicle Migration:	None	AAMA 800-92
Hardness (Shore 00):	40-60	AAMA 800-92
Water Resistance:	Excellent	AAMA 800-92
Crazing to Acrylic Plastics:	None	MIL-S-11030 C
Service Temperature Range:	-50°F to 180°F (-45.55°C to 82.22°C)	
Shelf Life:	SM5700 Poly-Glaze® Tape Sealant will exhibit a 12 month shelf life when stored at temperatures not exceeding 80°F (26.7°C).	

SPECIFICATION COMPLIANCE:

AAMA 807.3-92 Reference Standards: ANSI AAMA 101-88 ANSI AAMA 1002-10-83

- b) If frame joinery (butt joint) is vertical, apply the tape on the head and sill sections covering this joint prior to applying tape to the jamb sections. If the joinery is horizontal apply the tape to jamb sections, covering the joint, prior to head and sill application. Seal all tape joints with SM5504 Narrow Joint Sealant.
- c) Setting blocks should have a Shore "A" hardness of 80-90. These should be placed at quarter points on the sill member. Prior to use, setting blocks and anti-walking blocks must be tested for sealant compatibility.
- d) Center the glass or panel in the opening on the setting blocks and press firmly against the tape.

PRECAUTIONS:

IF THIS PRODUCT IS USED IN DIRECT CONTACT WITH ANY OTHER SEALANT OR ELASTOMER, A COMPATIBILITY TEST MUST BE CONDUCTED, BY PURCHASER OR USER, PRIOR TO ACCEPTANCE.

The suitability of this product, for each intended use, must be determined by the purchaser or user prior to acceptance. Pretesting for adhesion will aid in determining proper surface preparation if necessary.

Refer to Material Safety Data Sheet (MSDS) for further information.

For medical emergency only,
Call: ChemTrec 1-800-424-9300

EXCLUSION OF WARRANTIES:

AS TO THE HEREIN DESCRIBED MATERIALS, SCHNEE-MOREHEAD, INC. MAKES NO WARRANTIES WHETHER EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SINCE THE USE OF THE HEREIN DESCRIBED MATERIALS INVOLVES MANY VARIABLES IN METHODS OF APPLICATION, HANDLING AND/OR USE, THE USER IN ACCEPTING AND USING THESE MATERIALS ASSUMES ALL RESPONSIBILITY FOR THE END RESULT. THE PURCHASE OF THIS SCHNEE-MOREHEAD, INC. PRODUCT IS SUBJECT TO THE TERMS AND CONDITIONS OF AN "AS IS" SALE, AND IF THE PRODUCT IS PROVED TO BE DEFECTIVE, THE EXCLUSIVE REMEDY, AT SCHNEE-MOREHEAD, INC.'S OPTION, SHALL BE TO REPLACE THE DEFECTIVE SCHNEE-MOREHEAD, INC. PRODUCT. SCHNEE-MOREHEAD, INC. SHALL NOT OTHERWISE BE LIABLE FOR LOSS OF DAMAGES, WHETHER DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL, REGARDLESS OF THE LEGAL THEORY ASSERTED, INCLUDING NEGLIGENCE, WARRANTY OR STRICT LIABILITY.

Complete technical information is available from Schnee-Morehead, Inc. For technical assistance, customer service and general information call:

1-800-TRUSTSM
1-800-878-7876

SCHNEE-MOREHEAD, INC.

An *ITW* Company
111 N. Nursery Road
Irving, TX 75060
972-438-9111 Fax: 972-554-3939
www.trustsm.com